


FORTIDE®-HT

Product information



Two-component epoxy coating for high operating temperatures



Specific advantages:



For operating temperatures up to +150 °C (+302 °F).



Fulfils ISO21809-3, type 18-A.



Free from volatile solvents and isocyanates.



Brush or spray application



Excellent cathodic disbondment resistance.

Product description

FORTIDE®-HT is a durable corrosion prevention system for buried and submerged pipelines which has been specifically designed for **use in high temperature ranges**.

FORTIDE®-HT features **outstanding hardness** while also providing **good abrasion resistance**.

FORTIDE®-HT covers a very broad range of applications,

thanks to its ease of use in a variety of ways.

The product is available in both spray and brush variants.

The isocyanate- and solvent-free system ensures **compliance with the most stringent environmental and health and safety requirements**.

FORTIDE®-HT fulfils the requirements of **ISO 21809-3, type 18A**.

The coating's durability is a result of its outstanding temperature resistance, excellent **resistance to cathodic disbondment** combined with **exceptional indentation strength**.

FORTIDE®-HT is available in different package sizes, which means that a practical and economical size is available depending on the requirements of the project.

Typical product properties

Property	Unit	Typical value	Required value	Test method	
Type	-	two components	-	ISO 21809-3	
Colour	-	red brown	-		
Recommended minimum layer thickness	µm	≥ 750	-		
Theoretical consumption for 750 µm DFT	kg/m ² l/m ²	1.03 0.76	-		
Indentation resistance (10 N/mm ² , stamp-Ø 1.8mm)	+150 °C (+302 °F)	% of the original thickness	≤ 10		≤ 30
Cathodic disbondment	+23 °C (+73 °F)	mm	≤ 2		≤ 8
	+95 °C (+203 °F)		≤ 5		≤ 15
Hardness	+23 °C (+73 °F)	Shore D	≥ 80		-
Adhesion	EP on steel	MPa	≥ 15		≥ 10
	EP on EP				
Adhesion after hot water immersion (28 d / +95 °C / +203 °F)	EP on steel		≥ 11	≥ 7	
	EP on EP		≥ 11	≥ 2	

Processing conditions

Brush application				
Ambient and substrate temperature approx.		+10 °C (+50 °F)	+20 °C (+68 °F)	+40 °C (+104 °F)
Small package (brush variant)	Pot life (250 g total mass)	approx. 2 h	approx. 30 min.	approx. 18 min.
	Tack-free	approx. 5 h	approx. 2 h	approx. 45 min.
	durable	approx. 24 h	approx. 8 h	approx. 1.5 h
Hot airless spray application				
Ambient and substrate temperature approx.		+10 °C (+50 °F)	+20 °C (+68 °F)	+55 °C (+131 °F)
Hobbock (hot airless spraying)	Tack-free	approx. 4 h	approx. 1.5 h	approx. 30 min.
	durable	approx. 16 h	approx. 5 h	approx. 1 h
General processing conditions				
Processing temperature	Substrate	≥ +10 °C (≥ +50 °F); min. +3 °C (+5.4 °F) above the dew point		
	Environment	-40 °C to +50 °C (-40 °F to +122 °F)		
Steel surface	Degree of cleanliness (ISO 8501-1)	min. Sa 2 ½		
	surface roughness (ISO 8503-1)	40 – 100 µm		
Relative humidity	≤ 80 %			

Ordering information and packaging

Product name	Component Packaging	Contents per package approx.		Content per box
		[l]	[kg]	[pcs.]
FORTIDE®-HT 0.8 l Kit	Comp. A / B (cans)	0.6 / 0.2	0.9 / 0.2	12 / 12
FORTIDE®-HT 1.2 l Kit	Comp. A / B (cans)	0.9 / 0.3	1.3 / 0.3	8 / 8
FORTIDE®-HT	Comp. A / B (hobbock)	29 / 29	42 / 30	-
	Comp. A / B (barrel)	207 / 207	298 / 213	-

Storage

FORTIDE®-HT can be stored in its unopened original packaging for at least 12 months from the date of manufacture. Storage temperature: +5 °C (+41 °F) to +30 °C (+86 °F). Store in a dry and frost-free location.

DENSO GmbH

Felderstrasse 24 | 51371 Leverkusen | Germany
Phone: +49 214 2602-0 | info@denso-group.com
www.denso-group.com

Our product information, recommendations for use and other publications provide advice that is, to the best of our knowledge, factually correct, and reflects the latest information available to us on the date of printing. However, the contents of such publications are not legally binding. For this reason, no liability is accepted for inaccurate advice or any failure to provide advice. The user is responsible for checking the applications of the product and verifying its suitability for the intended purpose.

Unless otherwise specified, all of the brands mentioned are, at least in Germany, trademarks of DENSO and are protected by law. Our general terms and conditions of sale, which can be found at www.denso-group.com, apply exclusively to all transactions. The place of jurisdiction is Leverkusen/Germany.